



GRAFITACK 200/300 Plus SERIES GLOSSY COLOURS

**REFERENCES 210 to 248 (except for
225 & 226) and 328 to 337**

Realized on 1st July 2006



Description

The Grafitack 200/300 series is a soft cadmium-free polymeric calendered PVC film, provided with a pressure-sensitive permanent acrylic adhesive. This adhesive is protected by a high-quality silicone paper. A good recognizability is guaranteed by the red print on the material's backing paper.

Composition

- Film : 75 micron thick polymeric calendered PVC film
- Adhesive : permanent pressure-sensitive solvent-based acrylic adhesive, with a high resistance against UV-radiation, chemical products and humidity.
- Backing paper : siliconised white clay-coated paper of 120 gr/m²

Application

The Grafitack 200/300 series was developed for all indoor applications of up to 7 years when applied on a flat, unribbed background, such as sign making on cars, boats and trucks, for decorations of shop windows and advertisement boards. It is also perfect for everyday advertising indoors and outdoors.

Product advantages

A wide range of sparkling colours guarantees a magnificent end result every time again.

Product specifications

Technical properties at a relative humidity of 50 ± 5 % and a temperature of 23 ± 2°C.

		Test method	Result
1.	Thickness¹ Thickness vinyl Thickness vinyl + glue + backing paper	Din53370 Din53370	75 micron 240 micron
2.	Elongation at break² In production-length direction In cross direction	Din53455 Din53455	> 120 % > 140 %
3.	Dimensional stability³	Finat 14	< 0.40 %
4.	Degree of gloss Minimum (measuring angle 80°)	Din67530	50 %
5.	Adhesion strength⁴ After 20 minutes After 24 hours	Finat 1 Finat 1	15 N/25mm 16 N/25mm
6.	Quickstick⁵	Finat 9	9 N
7.	Expected outdoor life span⁶	-	7 years (colour 5-7 years)
8.	Temperature range At application At use	- -	+5°C to +40°C -25°C to +80°C
9.	Colour back print	-	red
10.	Flammability If applied on aluminium, glass, steel = self-extinguishing		

Storage instructions

All Grafitack materials always need to be stored in their original packing and with the original protection flanges (and preferably stored vertically).

In order to avoid any loss of quality, the Grafitack materials should also be stored in suitable conditions, that is at a temperature between 10 and 20°C, and a relative humidity of 50%.

Under these conditions, the Grafitack materials can be stored up to two years.

Remarks

In order to achieve an optimal result, we advise you to clean the surface with isopropanol and/or to use a low-tack application tape !

Important

The information, mentioned in this product data sheet, is based upon tests that were executed by Grafityp, and that we consider to be reliable. The information always represents an average, a minimum or a maximum value, and should be considered as such. It is only given for your information, and does not give any guarantee. It is up to the end user to decide whether or not the product is suited for his particular application.

1)
The thickness of the Grafitack materials may vary slightly. The indicated value is an average value, obtained from a series of measurements, in which a tolerance of 10 % is acceptable.

2)
The elongation at break of the Grafitack materials may vary slightly. The indicated value is a minimum value, obtained from a series of measurements.

3)
The dimensional stability is the shrinkage of the unprinted material in %. This value is measured by applying the film on aluminium, and placing it in a hot-air oven at 70°C for 48 hours (= Finat 14 Method, adjusted according to our own internally developed procedure). The indicated value is a maximum value, obtained from a series of measurements.

4)
The adhesion strength is measured on glass, and this after 20 minutes and after 24 hours. The film is removed again in an angle of 180° and at a speed of 300 mm/sec. The indicated value is an average value, obtained from a series of measurements.

5)
The "Quickstick" is the direct adhesion strength, measured on glass. The indicated value is an average value, obtained from a series of measurements.

6)
The expected outdoor life span refers to outdoor use under Central European conditions and to vertical applications. The expected life span of our films is based upon professional application on a dry, degreased and suitable background. Tropical conditions, or the use near chemical emission, may have a detrimental effect on the life span. The life span can also differ, depending on the colour (due to the pigmentation).



GRAFITACK 200/300 SERIES METALLIC COLOURS

REFERENCES 225 & 226

Realized on 1st July 2006



Description

The Graftack films with reference 225 and 226 are two metalised polyester films, provided with a pressure-sensitive permanent acrylic adhesive. This adhesive is protected by a high-quality silicone paper. A good recognizability is guaranteed by the red print on the material's backing paper.

Composition

- Film : 50 micron thick metalised polyester film
- Adhesive : permanent pressure-sensitive solvent-based acrylic adhesive, with a high resistance against UV-radiation, chemical products and humidity.
- Backing paper : siliconised white clay-coated paper of 120 gr/m²

Application

The Graftack films with reference 225 and 226 enable you to create the most stunning gold and silver decorations for indoor use.

Product advantages

Magnificent metall gloss.

Product specifications

Technical properties at a relative humidity of 50 ± 5 % and a temperature of 23 ± 2°C.

		Test method	Result
1.	Thickness¹		
	Thickness vinyl	Din53370	50 micron
	Thickness vinyl + glue + backing paper	Din53370	205 micron
2.	Elongation at break²		
	In production-length direction	Din53455	155 %
	In cross direction	Din53455	155 %
3.	Dimensional stability³	Finat 14	< 0.40 %
4.	Degree of gloss		
	Minimum (measuring angle 20°)	Din67530	60 %
5.	Adhesion strength⁴		
	After 20 minutes	Finat 1	12 N/25mm
	After 24 hours	Finat 1	12 N/25mm
6.	Quickstick⁵	Finat 9	3 N
7.	Expected outdoor life span⁶	-	not applicable
8.	Temperature range		
	At application	-	+5°C to +40°C
	At use	-	-20°C to +150°C
9.	Colour back print	-	red
10.	Flammability		
	If applied on aluminium, glass, steel = self-extinguishing		

Storage instructions

All Grafitack materials always need to be stored in their original packing and with the original protection flanges (and preferably stored vertically).

In order to avoid any loss of quality, the Grafitack materials should also be stored in suitable conditions, that is at a temperature between 10 and 20°C, and a relative humidity of 50%.

Under these conditions, the Grafitack metallic materials can be stored up to one year.

Remarks

In order to achieve an optimal result, we advise you to clean the surface with isopropanol and/or to use a low-tack application tape !

Important

The information, mentioned in this product data sheet, is based upon tests that were executed by Grafityp, and that we consider to be reliable. The information always represents an average, a minimum or a maximum value, and should be considered as such. It is only given for your information, and does not give any guarantee. It is up to the end user to decide whether or not the product is suited for his particular application.

1)
The thickness of the Grafitack materials may vary slightly. The indicated value is an average value, obtained from a series of measurements, in which a tolerance of 10 % is acceptable.

2)
The elongation at break of the Grafitack materials may vary slightly. The indicated value is a minimum value, obtained from a series of measurements.

3)
The dimensional stability is the shrinkage of the unprinted material in %. This value is measured by applying the film on aluminium, and placing it in a hot-air oven at 70°C for 48 hours (= Finat 14 Method, adjusted according to our own internally developed procedure). The indicated value is a maximum value, obtained from a series of measurements.

4)
The adhesion strength is measured on glass, and this after 20 minutes and after 24 hours. The film is removed again in an angle of 180° and at a speed of 300 mm/sec. The indicated value is an average value, obtained from a series of measurements.

5)
The "Quickstick" is the direct adhesion strength, measured on glass. The indicated value is an average value, obtained from a series of measurements.

6)
The expected outdoor life span refers to outdoor use under Central European conditions and to vertical applications. The expected life span of our films is based upon professional application on a dry, degreased and suitable background. Tropical conditions, or the use near chemical emission, may have a detrimental effect on the life span. The life span can also differ, depending on the colour (due to the pigmentation).